

TECHNICAL DATA SHEET TDS: TMP101B
TEAMALAK HIGH PERFORMANCE VARNISH **507/P101**

DESCRIPTION:

Our Teamalak High Performance Varnish is our most durable marine varnish. It is a 2 pack polyurethane coating that can extend the lifespan of your boat providing outstanding scratch resistance and UV protection. It's easy to clean finish assists fungal and algae growth removal.

RECOMMENDED USE:

Teamalak High Performance Varnish is suitable for yachts, power boats, dinghies, narrowboats, cruisers, commercial vehicles and many other marine applications. It can be applied to suitably prepared wood, steel and correctly prepared aluminium (It cannot be applied directly to existing solvent based coatings).

AVAILABILITY:

5 litre mixed packs

FINISH:

High Gloss

COLOUR:

Clear

TYPICAL S.G. (SPECIFIC GRAVITY):

1.07 @ 20 °C

VOLUME SOLIDS:

47%

WET FILM THICKNESS W.F.T

125 microns

DRY FILM THICKNESS D.F.T

60 microns

EXPECTED SPREADING RATE:

8 sq.m / litre
@ 60 microns D.F.T

The practical spreading rate may be lower as this depends on factors such as the porosity and roughness of the surface to be painted and material losses during application.

TYPICAL VISCOSITY:

N/A

FLASH POINT:

40 °C (closed cup)

CURE TIME: @ RECOMMENDED D.F.T

Initial cure: 3 to 4 hours @ 20 °C

Hard dry: 16 to 24 hours @ 20 °C

Full cure: 5 to 7 days @ 20 °C

Low temperature and high humidity will adversely affect application, curing and performance of any coating.

POTLIFE:

6 to 8 hours @ 20 °C

Pot Life - Once the parts are mixed together the material has to be used within the time stated.

MINIMUM OVERCOATING TIME:

Minimum 16 hours

APPLICATION SPECIAL CONDITIONS:

See Application Conditions.

VOC CONTENT:

Max 498 g / litre

VOC's (Volatile Organic Compounds) contribute to atmospheric pollution

APPLICATION DETAILS:

Application See Application Conditions.
restrictions

Method: Brush or short nap mohair roller. Airless Spray roller.

For further advice contact Teamac Technical Services on +44(0)1482 320194

The physical constants are subject to normal manufacturing tolerances.

"COVERING OUR CUSTOMERS' NEEDS SINCE 1908"

TEAMALAK HIGH PERFORMANCE VARNISH

507/P101

Thinner Do Not Thin. Do Not Thin.
(Max vol):

Nozzle size: 0.013"

Nozzle pressure: 1800 to 2000 psi

Cleaning solvent: HP Finish Thinners 7

Recoat interval: Minimum 16 hours Maximum 72 hours

suitable protective clothing and separate air fed breathing apparatus. It is recommended that spraying of these products be avoided wherever possible to facilitate uncomplicated application and site conditions.

PRECEDING COAT:

Apply direct.

SUBSEQUENT COAT:

Teamalak High Performance Varnish - for best results apply 2 to 3 coats.

REMARKS:

Not for use over conventional solvent based paints or varnishes.

SURFACE PREPARATION:

All surfaces should be clean, dry, sound and free from contaminants. Wood should be sanded prior to coating to ensure an adequate "key" is produced. Not for use over conventional solvent based varnishes.

MIXING INSTRUCTIONS:

The product is supplied in two containers: one larger than the other and labelled Base. The other smaller one labelled Activator. The contents of the pack marked Activator are added to the contents of the larger pack marked Base and thoroughly mixed together, preferably by slow speed electric mixer for 2 minutes or until thoroughly mixed. Failure to mix the material correctly will lead to uncured areas in the coating.

HEALTH AND SAFETY:

For activator see safety data sheet - SDS 10750. For base see safety data sheet - SDS 10749.

ISSUED:

25 November 2019

REVISION:

0

APPLICATION CONDITIONS:

Apply between 5°C to 30°C by brush or short nap mohair roller. This product can also be spray applied in approved conditions. When brush or roller applied at ambient temperatures - these products do not emit free Isocyanate at above levels recommended by C.O.S.H.H. Regulations. However, the protective measures shown on the product labels and safety data sheets must be followed. When used at elevated temperatures or atomised (sprayed) these products do emit small amounts of free Isocyanate and should only be sprayed in an atmosphere controlled working area, with suitable ventilation or flame proof extraction of air. Operatives must wear

The information given in this data sheet is based on experience and is accurate to the best of our knowledge. No guarantee should be implied, however, as the conditions of use are beyond our control. This data sheet does not constitute a specification. In case of doubt as to the suitability of the product please contact our Technical Service Department on 01482 320194.

For further advice contact Teamac Technical Services on +44(0)1482 320194

The physical constants are subject to normal manufacturing tolerances.

"COVERING OUR CUSTOMERS' NEEDS SINCE 1908"

TEAMAC

Lockwood Street, Hull HU2 0HN

Tel.: +44(0)1482 320194. Fax: +44(0)1482 219266

Email: info@teamac.co.uk

www.teamac.co.uk